



Wayne Pigment Corp.

300 South Barclay Street Milwaukee, Wisconsin 53204  
Phone 414/225-2400 FAX 414/225-2410

www.waynepigment.com  
E-mail: genoffice@waynepigment.com

200PDS1.B03

# Product Data Sheet

Page 1 of 1

## Mirrorstop 201

### CORROSION INHIBITIVE PIGMENT FOR MIRROR BACK COATINGS

<u>Characteristic Parameters</u>	<u>Typical Values</u>
Appearance	White Powder
Specific Gravity	2.50 - 2.70
Bulking Value (gal/lb)	0.044 - 0.048
Oil Absorption (lbs/100 lbs)	22 -28
pH	7.5 -8.5
Moisture, % (loss on ignition, 110 EC)	< 5.0

The recommendations made herein are based on our research and on the research of others; and are believed to be accurate. No guarantee of the accuracy is made, however, and the products discussed are sold without warrant, expressed or implied, and upon the condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes.